



INTERNATIONAL GEMOLOGICAL INSTITUTE

SCIENTIFIC LABORATORY FOR THE IDENTIFICATION AND GRADING
OF DIAMOND AND COLORED STONES

EDUCATIONAL PROGRAMS

Expertise issued by I.G.I. bvba

Head Office and Laboratories:

1/7 Schupstraat, 2018 Antwerp - Belgium

Tel: +32 3 401 08 88 - Fax: +32 3 232 07 58

E-mail: info@igworldwide.com

www.igworldwide.com

DIAMOND REPORT

This report is a statement of the diamond's identity
and grade including all relevant information.

NUMBER F6D26594

ANTWERP, June 27, 2012

LABORATORY REPORT (ORIGINAL)

TO WHOM IT MAY CONCERN.

DESCRIPTION
SHAPE AND CUT
CARAT WEIGHT
COLOR GRADE
CLARITY GRADE
CUT GRADE

POLISH
SYMMETRY

NATURAL DIAMOND
ROUND BRILLIANT
1.00 CARAT
F
VVS 2
VERY GOOD

VERY GOOD
GOOD

Measurements

6.19 - 6.26 x 4.08 mm

Table

56.5%

Crown Height - Angle

16% - 36.5°

Pavilion Depth - Angle

44.5% - 41.6°

Girdle Thickness

MEDIUM TO THICK (FACETED)

Culet

POINTED

FLUORESCENCE

NONE

The symbols do not usually reflect the size of the characteristics.

Red symbols indicate internal characteristics.

Green symbols indicate external characteristics.



Important external details, visible under
high magnification only, are not shown.



Truth values included in this document are subject
to reworked cases and additional requests for tests
for a complete correct result security protocol.

CLARITY GRADE: Internally Flawless VS₁ VS₂ VS₁ VS₂ S₁ S₂ I₁ I₂ I₃

COLOR GRADE: D E F G H I J K L M N O P Q R S-Z FANCY COLOR

PROPORTIONS - MARGIN: ± 1%

MEASUREMENTS - MARGIN: ± 0.02mm

The gemological analysis of diamonds, precious stones and other minerals must be carried out by gemologists with many years experience. In this field who have a keen sense of the professional code of ethics governing their work as well as a thorough knowledge of crystallographic, optical and physical phenomenon.

The identification of the various species and varieties of stones, the distinction between natural and synthetic material, as well as various treatment methods currently encountered are all very sensitive factors. More specifically for diamonds, the laws of refraction and dispersion of light, the related geometric data as well as knowledge of all aspects involved in the cutting process are essential.

This gemological report is provided upon request of the customer and/or the owner of the gem. By making this report I.G.I. does not agree to purchase or replace the article. Neither I.G.I. nor any member of its staff shall, at any time, be held responsible for any discrepancy which may result from the application of other grading methods. Neither the client nor any purchaser of the gem shall regard this Report as an appraisal nor as a guaranty or warranty.

This report is subject to the terms and conditions set forth above and on reverse.

© I.G.I., 2000, edition 2011

All rights reserved. No part of this report may be reproduced or transmitted in any form or by any means, without permission in writing from International Gemological Institute.